

TUNGSTEN CARBIDE COATINGS AND PROCESS FOR PRODUCING THEM

Abstract

5

New tungsten carbides alloyed with fluorine in amounts up to 0.5 wt% and possibly with fluorocarbon compositions are described. It is possible to produce them by means of a new process of chemical vapour deposition, in which tungsten hexafluoride, hydrogen and a carbon-containing gas are used. A specific feature of the new process is the preliminary thermal activation of the carbon-containing gas.

10

The tungsten carbide coatings are deposited on construction materials and items made from them. They possess enhanced resistance to wear, corrosion and chemicals.

15

20

P45043wo.spc as filed